

AD-A082 848

PRINCETON UNIV NJ JOSEPH HENRY LABS OF PHYSICS
A THEORY OF GLASSY SEMICONDUCTORS.(U)
APR 80 D C LICCIARDELLO

F/G 20/12

N00014-77-C-0711

NL

UNCLASSIFIED

1 2 3 4 5 6 7 8 9 10 11 12



END
DATE
FILMED
5-80
DTIC

ADA 082848

DOC FILE COPY

UNCLASSIFIED		LEVEL 12	
SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)		READ INSTRUCTIONS BEFORE COMPLETING FORM	
REPORT DOCUMENTATION PAGE			
1. REPORT NUMBER	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER	
4. TITLE (and Subtitle) A THEORY OF GLASSY SEMICONDUCTORS.		5. TYPE OF REPORT & PERIOD COVERED technical report, 1979	
7. AUTHOR(s) D.C. LICCIARDELLO		8. CONTRACT OR GRANT NUMBER(s) N00014-77-C-0711	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Department of Physics, Princeton University Princeton, N.J. 08544		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR 318-058	
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research (Code 427) Arlington, Va. 22217		12. REPORT DATE April 1, 1980	
13. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) W. C. I.		14. NUMBER OF PAGES 9 pages + 3 Figures	
		15. SECURITY CLASS. (of this report) Unclassified	
		16a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.			
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report) DTIC ELECTE S APR 9 1980 E			
18. SUPPLEMENTARY NOTES Invited talk by the Solar Energy Research Inst. To be published as part of the proceedings of the Amorphous Silicon Workshop San Diego, January, 1980			
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) amorphous semiconductors glassy semiconductors negative U model localization			
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) A model for glassy semiconductors is discussed which provides for a generic description of a wide range of materials. The theory is based on the premise that the under lying disorder of the amorphous state requires a qualitatively different description. The major consequence of the lack of long-range structural symmetry is the enhancement of the electron-phonon interaction and the localization of eigenstates. Strong enough interaction leads to an effective attraction between localized electrons which accounts for both diamagnetism and			

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0107-LF-014-6601

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

405627

Abstract (cont'd.)

optical transparency. The excitations on the ground state are derived and consideration of their relaxation leads to the existence of long lived states in a narrow region of the spectrum near the Fermi level.

Accession For	
NTIS GRA&I	<input checked="checked" type="checkbox"/>
DDC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Available/or special
A	

A Theory of Glassy Semiconductors*

D.C. Licciardello

(Joseph Henry Laboratories of Physics)
Princeton University
Princeton, New Jersey
08544

ABSTRACT

A model for glassy semiconductors is discussed which provides for a generic description of a wide range of materials. The theory is based on the premise that the underlying disorder of the amorphous state requires a qualitatively different description. The major consequence of the lack of long-range structural symmetry is the enhancement of the electron-phonon interaction and the localization of the eigenstates. Strong enough interaction leads to an effective attraction between localized electrons which accounts for both diamagnetism and optical transparency. The excitations on the ground state are derived and consideration of their relaxation leads to the existence of long lived states in a narrow region of the spectrum near the fermi level.

80 4 8 014

We describe here a simple theory of amorphous semiconductors which, we believe, is applicable to a wider range of glassy materials. The approach is substantially different from the generally accepted point of view^[1] in which defects in an otherwise ideal material play the dominant role. Described elsewhere^[2] in these proceedings, the defect model supposes that an ideal random network (for a covalently bonded material, for example) would give rise to a similar electronic structure to the corresponding crystal except for small band tailings at band extrema. The real material, however, is interrupted by a set of thermodynamically stable defects where the valence requirements are not satisfied. The corresponding states will lie in the gap and thus determine much of the observed electrical and optical properties. In our picture, disorder is assumed to be severe so that the fundamental electronic energy distribution, in the ground state, contains no structure. More precisely, we do not a priori suppose the existence of an energy gap in the electronic spectrum. Thus the optical gap observed in these materials will follow from a different mechanism.

Our model^[3] bears at least a family resemblance to the Cohen-Fritzsche-Ovshinski^(CFO) band picture for amorphous semiconductors described some years ago.^[4] These authors assumed that band tailings from the conduction and valence bands would be significant enough to completely wipe out the gap. The density of states at the fermi level $N(E_F)$ was supposed finite due to band tail overlap. Indeed, experimentally it remains a more or less universal property of virtually all glassy semiconductors that the fermi level is pinned : that the states in the conduction or valence band do not control the position of E_F . Thus such materials generally give rise to a large density of states at E_F . Hydrogenated amorphous silicon

provides the one counter-example where the material has been shown to be dopable to a limited extent. This, of course, is why there is a current flurry of interest in this system. We shall argue that even in this case, however, many of the considerations we discuss are relevant.

Perhaps the most convincing evidence exists in the class of chalcogenide glasses where, for a wide range of materials, the optical gap roughly equals twice the conductivity activation energy.^[1] This implies that E_F is pinned near mid-gap which is easy to understand within the CFO picture. The defect model would, by contrast, require a surprising correlation of defect energies to explain this effect.

The main consequences of an approach which assumes severe randomness is twofold: 1) electron localization and associated mobility edge phenomena, and 2) the enhancement of the electron phonon interaction. The first follows from well established theoretical considerations, first elucidated by Anderson for a simple model.^[5] Although there is no similar first principles evidence for a disorder induced electron-phonon coupling, even within a simple model, Emin^[6] and Mott and Davis^[1] have argued that much of the transport data on glassy systems can be understood in terms of a polaronic picture. The enhancement of the lattice interactions is due, in part, to the reduced electron mobility observed generally in these materials.

We describe some of the implications of a model, first introduced by Anderson,^[7] in which both localization and a strong lattice coupling are explicitly included. We consider a spatially random distribution of localized eigenstates characterized by an energy ϵ_i (also random) for the i^{th} state. Each state may be occupied by up to two electrons. The coulombic repulsion at double occupancy is treated by a Hubbard-like term

characterized by an energy U_i for the i^{th} site. We ignore the intersite electrostatic interaction. The coupling of the electron to local phonon modes is taken explicitly through terms linear in the electron occupation operator n_i and the phonon field b_i^+ for creating a phonon at the i^{th} site. In the absence of an intersite transfer matrix element for the phonons or the electrons, this term is easily diagonalized^[3] and gives attractive terms quadratic in the occupation n_i . Thus for the i^{th} site occupied by n_i electrons, the energy E_{n_i} is given by

$$E_{n_i} = n_i \epsilon_i + U_i \delta_{2,n_i} - \frac{1}{2} C_i n_i^2 \quad (1)$$

Here C_i describes a lattice-mediated attractive interaction energy between two electrons at the site i which occurs in the Hamiltonian on the same footing as the Hubbard U_i . The factor $1/2$ accounts^[3] for the renormalization of the energy term ϵ_i due to the lattice coupling.

In addition, there is the usual phonon contribution to the energy. Recalling that we only consider local phonon modes we may represent all the contributions on an energy-configuration diagram shown in Figure 1. The diagram refers to a single site occupied by $n = 0, 1$, or 2 electrons with energies given according to eq. (1). The case shown assumes $E > \frac{1}{2} C$ and $C > U$ where the i index has been suppressed. We observe that the local configuration is displaced according to occupation due to the lattice coupling. For a given occupation, however, corresponding to a particular configuration, the energy is increased quadratically in the presence of a coordinate displacement. Thus the model includes local minima leading to metastabilities as discussed below.

The model is constructed from a collection of such sites in which the parameters U_i , C_i , and E_i vary randomly from site to site. It is

easy to show^[3] for a strongly coupled system in which $C_i > U_i$ for all i that, in the ground state, all sites contain $n_i = 2$ or 0 electrons according to their energy. It is convenient to set the energy scale so that the pair with the highest energy, which occurs at site j , satisfies

$$2\varepsilon_j + U_j - 2C_j = 0.$$

Our assumption on the electronic structure requires that the density of pairs with energies close to this is large. We may define a density of pair states $\rho(E_2)$ in which the energy E_2 of such a state refers to two electrons and is given through eq. (1). The chemical potential μ for adding a pair of electrons to the system vanishes according to our energy scale. This spectrum is displayed in the non-shaded region of Figure 2 and we note that there is no gap for pair excitations. Anderson has already pointed out that the absence of any gap in this spectrum can lead to a linear temperature term in the specific heat which has been observed generally in glassy systems.

In addition to this spectrum we may consider single-particle excitations which are relevant for optical absorption. For simplicity, we ignore the distributions in C_i and U_i and take them equal to some average value keeping $\langle C_i \rangle > \langle U_i \rangle$. We consider the process in which an electron is transferred from site i to site j through the absorption of a single photon. Thus each site will change its occupation by one particle. Since the absorption will occur on a time scale which is much faster than the period of a typical phonon oscillation, the configuration of each of the two sites will not change during the process. Thus each site, at its final occupation, will be displaced to the configuration of its initial occupation and this requires an additional energy $\frac{1}{2} C$. The energy for the process in which an electron is transferred from site i to

site j requires the contributions from an electron excitation at site j , Δ_j^e and a hole excitation at site i , Δ_i^h , given by

$$\Delta_j^e = E_{n_j+1} - E_{n_j} + \frac{1}{2} C \quad (2a)$$

$$\Delta_i^h = E_{n_i-1} - E_{n_i} + \frac{1}{2} C \quad (2b)$$

where the energies E_n are obtained from (1). In the ground state, the only allowable sites correspond to $n_i = 2$ and $n_j = 0$. The minimum energy for this occurs for sites at the fermi level of the $\rho(E_2)$ distribution (Figure 2) where $E_2 = 2\varepsilon + U - 2C = 0$ or $\varepsilon = C - U/2$. Substituting in eq. (2) we find

$$\Delta_i^e = \Delta_j^h = C - U/2. \quad (3)$$

which gives particle hole symmetry. Thus an optical gap exists and we predict that the fermi level will be pinned at midgap. This situation is observed generally in the class of chalcogenide glassy semiconductors.

We include both particle and hole excitations on a single particle excitation spectrum, shown in Figure 3, in which electron excitations appear for excitation energies $\Delta > 0$ and hole excitation energies are displayed with energies $\Delta < 0$. The solid curve represents the ground state excitations described above and the gap is evident with full width $2C - U$. Note that this is larger than the absolute gap in the single particle excitation spectrum (not shown) which must be equal to $C - U$ or just the effective binding of the two electrons in the pair. This, of course, is due to our requirement of an optical process in the analysis above.

We have further evaluated the excitations on a system prepared in a non-equilibrium metastable state. The state is determined by occupying all empty states above the fermi level with one or two electrons and all states below the fermi level (where $n = 2$ is the ground state) with one or two holes. Those states whose excited occupations require an absorption of a phonon or photon in order to relax to a state with a different occupation are termed metastable. States which will spontaneously change their occupation (with the absorption of any number of electrons or holes) with a phonon emission are unstable. If we ignore the energy of the absorbed particle, the condition for metastability for n particles (or holes) is given by

$$\Delta_n^{e,h} > 0 \quad (4)$$

where $\Delta_n^{e,h}$ is defined by equation 2. This is a somewhat conservative estimate for metastability since, as shown above, a gap exists in the single particle spectrum and thus for absorptions involving $n = 1$, the electron or hole is only available for energies above the gap. On the other hand, for a severely perturbed state there will be metastable single particle states occupied at the fermi level and so our estimate is self-consistent.

The metastable bandwidths are determined by setting

$$\Delta_n^{e,h} = 0 \quad (5)$$

For electron states we have

$$\begin{aligned} n = 2, \quad \Delta n &= -1, -2 \\ n = 1, \quad \Delta n &= -1 \end{aligned} \quad (6a)$$

and for hole states we have

$$\begin{aligned} n = 0, \quad \Delta n = +1, +2 \\ n = 1, \quad \Delta n = +1 \end{aligned} \quad (6b)$$

The solutions to (5) for each of these four conditions are shown in the shaded region of Figure 2. For electron states (with $E_2 > 0$) we may occupy the states between $0 < E_2 < 2C - U$ metastably with two electrons. The region is marked 2_0 where the subscript refers to the antecedent occupation (or ground occupation). Similar single electrons may persist in states in the range $0 < E_2 < U$ denoted by 1_0 . Single holes are metastable in the range $-U < E_2 < 0$ and two holes will metastably occupy those states in the range $-(2C-U) < E_2 < 0$ as denoted, respectively, by 1_2 and 0_2 . Thus the model is consistent with the observations of a photo induced spin.

More interesting is the effect of these metastabilities on the excitation spectrum. In the extreme case in which the least stable of the metastable states are occupied, that is, $|E_2| \approx 2C - U$ for $n = 2$, and $|E_2| \approx U$ for $n = 1$, we determine a complete collapse of the gap. This is shown in Figure 3 by the dashed region. The dashed density for excitation energies Δ in the range $0 < \Delta < U/2$ correspond to the process $1_2 + e \rightarrow 2_2$ (without relaxation), the range $U/2 < \Delta < U$ to the process $1_0 + e \rightarrow 2_0$ (without relaxation) and the dashed region $0 < \Delta < C - U/2$ corresponds to the process $0_2 + e \rightarrow 1_2$ (without relaxation). Fast hole excitations are also shown for $\Delta < 0$ and mirror the electronic ranges.

These metastabilities and the effect they have on optical excitations are consistent with a class of experiments performed on glassy chalcogenide semiconductors. These systems are well known to have photoinduced metastable states which give rise to a spin and a subgap absorption or photodarkening.

The lifetime of the metastability can be long (\sim days) experimentally which is entirely expected on the basis of the above considerations in which the energy scale is electronic (\sim eV) but the relaxation is thermal.

These considerations are entirely general and should apply to any diamagnetic glassy semiconductor including silicon-hydrogen alloys. The observed spin quenching on alloying can be understood within a negative-U model in which case the above analysis is relevant. The reduced density of states will not, of course, qualitatively affect these considerations. A specific negative-U configuration has already been proposed.^[8]

Acknowledgement

Research was supported in part by the National Science Foundation, Grant No. DMR 78-03015, and the Office of Naval Research, Grant No. N00014-77-C-0711.

References

- 1 N.F. Mott and E.A. Davis, Electronic Processes in Non-Crystalline Materials, Clarendon Press, Oxford, 1971.
- 2 D. Adler, Proceedings of Amorphous Silicon Workshop, San Diego, 1980.
- 3 D.C. Licciardello, D.L. Stein, and F.D.M. Haldane, Phil. Mag. (in press).
- 4 M.H. Cohen, H. Fritzsche, and S.R. Ovshinsky, Phys. Rev. Lett. 22, (1969) p. 1065
- 5 P.W. Anderson, Phys. Rev. 108, (1958) p. 1492
- 6 D. Emin in Amorphous and Liquid Semiconductors, W.E. Spear (ed.), Edinburgh, 1977, p. 249.
- 7 P.W. Anderson, Phys. Rev. Lett. 34, (1975) p. 953.
- 8 R. Fisch and D.C. Licciardello, Phys. Rev. Letters 41 (1978) p. 889.

Figure Captions

Figure 1 Energy/configuration diagram for a single lattice-coupled site. The three levels shown correspond, respectively, to electron occupation $n = 0, 1$ and 2 , which are displaced accordingly. For a given occupation, the energy of each level increases with change in configuration quadratically in the configuration parameter.

Figure 2 The density of pair states $\rho(E_2)$ as a function of pair energy E_2 in the ground state (solid curve). The shaded areas correspond to those regions of the spectrum where states occupied with N_m electrons (where m is the ground occupation) are metastable.

Figure 3 Single particle (fast) excitation spectrum. Electron excitations of energy Δ occur with $\Delta > 0$ and hole excitation with $\Delta < 0$. The ground states particle/hole excitation costs $\Delta = 2C - U$. The dashed region corresponds to excitations on metastable states. The dashed region $-U < \Delta < U$ defines fast processes on singly occupied metastable states and the dashed region in the range $-(C-U/2) < \Delta < C - U/2$ refers to metastable doubly occupied states.




Fig. 1

METASTABLE BANDS




Fig. 2

SINGLE PARTICLE EXCITATION SPECTRUM




Fig. 3